SM14304

Translucent Silicone FDA & EU 1935/2004 Grade 60° Shore

Item Code:

SM14304

Item Description:

Translucent Silicone FDA & EU1935/2004 Grade 60° shore

SM14004 Translucent Silicone Food & Drink Grade 60° shore is high quality sheeting for demanding applications with excellent heat and flame resistance together with very good aging and weathering characteristics and suitable for use with food and drink. Meets FDA 21 CFR No: 177 – 2600 - EU1935/2004 regulations and USP Class V1 Compliant

Material Profile: See Below
Thickness: 1.0mm to 20mm

Sheet Size: 1.2m wide in 5m and 10m rolls

· Finish: Smooth finish,

· Cutting: Standard press-tools

This Product is REACH, RoHS, PAH and CE Compliant

Other grades, colours and finishes are available - subject to minimum batch quantities

Technical Information					
Material	Silicone				
Application	Chemical Resistant, FDA APPROVED, Flame Resistant, Food / Drink, High Temperture, Weather / Ozone				
Shore Hardness +/- 5°	60				
Thickness	1mm, 1.5mm, 2mm, 3mm, 4mm, 5mm, 6mm, 8mm, 10mm, 12mm				
Temp Range	-60°C, -50°C, -40°C, -30°C, -20°C, -10°C, +70°C, +80°C, +90°C, +100°C, +110°C, +120°C, +125°C, +130° C, +140°C, +150°C, +160°C, +180°C, +200°C, +170°C, +225° c				
Colour	Translucent				
Insertion Req	No				
Cloth/Plate	Plate / Plate				
Resistant To	Please Call				



Item Code:

SM14304

The stock roll size chart represents our standard stock range and items stated are not subject to any minimum batch quantities. Other size requirements for thickness, width, length or finish can be made to special order but would be subject to minimum production batch runs.

This normally would be:-

1mm - 6mm thick - 100 linear metres,

8mm - 25mm thick - 50 linear metres,

Over 25mm thick - 10 sheets.

Further details given upon request.

Surface Finish Codes:-

SS - Smooth finish both sides

CC - Cloth Impression both sides

CS - Cloth impression one side, smooth the other



Stock Sheet Sizes	Surface	Weight	Specifications	Values
[m x m x mm]	[finish]	[kg/M2]	[compound]	[typical]
1mm x 1200mm x 10m	SS	1.20	Colour	Translucent
1.5mm x 1200mm x 10m	SS	1.80	Compound	SI
2mm x 1200mm x 10m	SS	2.40	Density [specific gravity]	1.20
3mm x 1200mm x 10m	SS	3.60	Hardness [Degrees Shore A]	60° ± 5°
4mm x 1200mm x 10m	SS	4.80	Tensile Strength Kg/cm2 [Polymer]	100
5mm x 1200mm x 10m	SS	6.00	Elongation at break %	250
6mm x 1200mm x 10m	SS	7.20	Minimum Temperature	-60°C
8mm x 1200mm x 5m	SS	9.60	Maximum temperature	+225°C
10mm x 1200mm x 5m	SS	12.00	Compression Set (70°C for 22 hours) %	
12mm x 1200mm x 5m	SS	14.40	Polymer Content %	100
15mm x 1200mm x 5m	SS	18.00		
20mm x 1200mm x 5m	SS	24.00		