

C-HPU 57D

Mechanical, Physical and Thermal Properties

thermoplastic polyurethane with resistance to hydrolysis

properties	condition	standard	unit		unit	
colour				yellow		yellow
hardness	23°C	ISO 868	Shore A		Shore A	
hardness	23°C/3 sec.	ISO 868	Shore D	57 ± 3	Shore D	57 ± 3
hardness	23°C/15 sec.	ISO 868	Shore D	53 ± 3	Shore D	53 ± 3
modulus 100%	23°C	DIN 53 504	MPa	≥ 20	psi	≥ 2900
modulus 300 %	23°C	DIN 53 504	MPa	≥ 33	psi	≥ 4785
tensile strength	23°C	DIN 53 504	MPa	≥ 45	psi	≥ 6530
elongation at break	23°C	DIN 53 504	%	≥ 350	%	≥ 350
tear strength	23°C	DIN ISO 34-1	kN/m	≥ 110	lbf/inch	≥ 630
spec. gravity	23°C	ISO 1183	kg/m ³	1160	g/cm ³	1,16
abrasion	23°C	DIN 53 516	mm ³	25	mm ³	25
compression set	*	ISO 815	%	≤ 30	%	≤ 30
compression set	**	ISO 815	%	≤ 35	%	≤ 35
minimum service temperature			°C	-30	°F	-22
maximum service temperature			°C	110	°F	230

* 24h 70°C 25% def.

** 24h 100°C 25% def.

CHEMICAL PROPERTIES

Copolymer, based on aromatic isocyanate and diols

Resistant to oil, hot water, ozone, microbes

Not resistant to conc. acids, conc. lyes, conc. alcohols and aromatic solvents

Detailed information concerning chemical resistance see Chemical Resistance Guide

DUBLIN

John F. Kennedy Rd
John F. Kennedy Ind Est
Dublin D12 PD36

T: +353 (0)1 427 7900
F: +353 (0)1 450 8181
E: dublin@abbeyseals.ie

CORK

31B Euro Business Park
Little Island
Cork T45 X310

T: +353 (0)21 500 3555
F: +353 (0)21 500 3554
E: cork@abbeyseals.ie