

FPM FDA

Mechanical, Physical and Thermal Properties

Fluoro Rubber

properties	condition	standard	unit	unit
colour			brown	brown
hardness	23°C/3 sec.	ISO 868	Shore A	80 ± 5
hardness	23°C/15 sec.	ISO 868	Shore A	77 ± 5
modulus 100%	23°C	DIN 53 504	MPa	≥ 6
tensile strength	23°C	DIN 53 504	MPa	≥ 8
elongation at break	23°C	DIN 53 504	%	≥ 150
tear strength	23°C	DIN ISO 34-1	kN/m	≥
spec. gravity	23°C	ISO 1183	kg/m³	2400
rebound elasticity	23°C	DIN 53 512	%	7
abrasion	23°C	DIN 53 516	mm³	220
compression set	*	ISO 815	%	≤ 7
compression set	**	ISO 815	%	≤ 9
compression set	***	ISO 815	%	≤ 14
minimum service temperature			°C	-20
maximum service temperature			°C	220
temp. max water/steam			°C	
temp. max hot air			°C	300 short
				°F
				572 short

* 24h 70°C 25% def.

** 24h 100°C 25% def.

*** 24h 175°C 25% def.

CHEMICAL PROPERTIES

Copolymer, based on fluoro

Resistant to: fats, crude oil, mineral oil, gasoline, aliphatic and aromatic hydrocarbons

Not resistant to: glycols, ketones, most fluids containing amines and water/steam

Foodstuff approval: FDA compliant in it's active substances to:

- the Positive List for water-based foods under the Section 177.2600, CFR 21, "Rubber Articles Intended For Repeated Use", of the Food and Drug Administration (FDA), USA
- the Positive List for fatty foods (including milk and cooking oil), under the Section 177.2600, § 21 CFR "Rubber Articles Intended For Repeated Use", of the Food and Drug Administration (FDA), USA

Detailed information concerning chemical resistance see Chemical Resistance Guide

DUBLIN

Unit B1
Nangor Road Business Park
Dublin D12 TNY6

T: +353 (0)1 427 7900
E: dublin@abbeyseals.ie

CORK

31B Euro Business Park
Little Island
Cork T45 X310

T: +353 (0)21 500 3555
E: cork@abbeyseals.ie