

POM BLACK

Mechanical, Physical and Thermal Properties

Polyoxymethelene/Polyacetal

properties	condition	standard	unit		unit	
colour				black		black
density/specific gravity	23 °C	DIN 53479	kg/m ³	1410	g/cm ³	1,41
hardness	23 °C	ISO 868	Shore D	81 ±3	Shore D	81 ±3
ball indentation hardness	23 °C	ISO 2039, Part 1 (F:358N)	MPa	144	psi	20885
tensile strength	23 °C	ISO 527	MPa	60	psi	8702
elongation at break	23 °C	ISO 527	%	30	%	30
compressive strength	23 °C	DIN 53455	MPa	88	psi	12800
thermal conductivity		DIN 52612	W/(m*K)	0,31	W/(m*K)	0,31
coefficient of thermal expansion	25 °C - 200 °C		K ⁻¹ * 10 ⁻⁵	11	K ⁻¹ * 10 ⁻⁵	11
coefficient of friction *	23 °C		μ	0,28	μ	0,28
minimum service temperature			°C	-45	°F	-49
maximum service temperature			°C	100	°F	212
young's modulus	23 °C	ISO 527	MPa	2500	psi	362594

* coefficient of friction dry dynamic Steel 16MnCr5 v=0,6m/s; p=0,05 MPa; t=5h

CHEMICAL PROPERTIES

Copolymer, based on methylenoxide

Resistant to fuels, water, lyes, lubricants, alcohols and solvents

Not resistant to strong mineral acids, oxidising chemicals, ethers; limited resistant to UV radiation and long term hot water

Detailed information concerning chemical resistance see Chemical Resistance Guide

DUBLIN

John F. Kennedy Rd
John F. Kennedy Ind Est
Dublin D12 PD36

T: +353 (0)1 427 7900
F: +353 (0)1 450 8181
E: dublin@abbeyseals.ie

CORK

31B Euro Business Park
Little Island
Cork T45 X310

T: +353 (0)21 500 3555
F: +353 (0)21 500 3554
E: cork@abbeyseals.ie