

PTFE D05

Mechanical, Physical and Thermal Properties

1 % pigments + 99 % virgin PTFE

properties	condition	standard	unit		unit	
colour				turquoise		turquoise
density/specific gravity	23 °C	DIN 53479	kg/m ³	2170	g/cm ³	2,17
hardness	23 °C	ISO 868	Shore D	57 ±3	Shore D	57 ±3
ball indentation hardness	23 °C	DIN 53456 H135/30	MPa	28 ±5	psi	4060 ±725
tensile strength	23 °C	ASTM D 4745-79	MPa	≥ 31	psi	≥ 4495
elongation at break	23 °C	ASTM D 4745-79	%	≥ 270	%	≥ 270
compressive strength	23 °C	DIN 53455	MPa	≥ 4	psi	≥ 580
thermal conductivity		DIN 52612	$\frac{J^* 10^3}{m^* h^* K}$	≥ 0,8	$\frac{J^* 10^3}{m^* h^* K}$	≥ 0,8
coefficient of thermal expansion	25 °C - 200 °C		K ⁻¹ * 10 ⁻⁵	≥ 19	K ⁻¹ * 10 ⁻⁵	≥ 19
coefficient of friction *	23 °C		μ	≥ 0,08	μ	≥ 0,08
minimum service temperature			°C	-200	°F	-328
maximum service temperature			°C	260	°F	500
young's modulus	23 °C	DIN 53457	MPa	≥ 540	psi	≥ 78500

* coefficient of friction dry dynamic Steel 16MnCr5 v=0,6m/s; p=0,05 MPa; t=5h

CHEMICAL PROPERTIES

Filled PTFE

Resistant to almost all chemicals

Not resistant to halogenides, elemental fluorine, CF₃, molten alkali metals

Foodstuff applications: FDA compliant

Detailed information concerning chemical resistance see Chemical Resistance Guide

DUBLIN

Unit B1
Nangor Road Business Park
Dublin D12 TNY6

T: +353 (0)1 427 7900
E: dublin@abbeyseals.ie

CORK

31B Euro Business Park
Little Island
Cork T45 X310

T: +353 (0)21 500 3555
E: cork@abbeyseals.ie